Yarn Count Conversion: Tex, Denier, Ne and Nm

Converts yarn linear density between tex, decitex, denier (direct systems) and English cotton count Ne and metric count Nm (indirect systems), from any one of them.

Method: Definitions and mass and energy balances: tex = g/1000 m; denier = g/9000 m; Ne = number of 840-yd hanks per lb; Nm = km/kg

Input parameters

Unit system: SI

Parameter	Value	Unit
Count entered in	Ne (English cotton)	
Count value	20.000	

Calculated results

Parameter	Value	Unit
Tex (g per 1000 m)	29.527	
Decitex	295.27	
Denier (g per 9000 m)	265.74	
English cotton count (840-yd hanks per lb)	20.000	
Metric count (km per kg)	33.867	

Formula and method

$$\mathrm{den} = 9\,\mathrm{tex}, \quad Nm = \frac{1000}{\mathrm{tex}}, \quad Ne = \frac{590.5}{\mathrm{tex}}$$

Variables

system	Count entered in	-
N	Count value	-
tex	Tex (g per 1000 m)	-
dtex	Decitex	-
den	Denier (g per 9000 m)	-
Ne	English cotton count (840-yd hanks per lb)	-
Nm	Metric count (km per kg)	-

Method and standards

Count definitions.

Assumptions and limits

- Single yarns; folded yarns need the resultant count.

References

• Definitions and mass and energy balances: tex = g/1000 m; denier = g/9000 m; Ne = number of 840-yd hanks per lb; Nm = km/kg

Report details

Report reference	FCC-VJC9-WQJ3 (the same inputs always give the same reference)
Generated	17 November 2026, 19:54 UTC
Calculator	Yarn Count Conversion: Tex, Denier, Ne and Nm
Method last reviewed	13 November 2026
Software release	FireCAD Calc, release of 17 November 2026
Release checks	3 reference cases of this calculator, computed independently, are checked on every release

Results are for engineering estimation. Verify critical designs against the referenced standards and your own data.

This calculator online

https://calc.firecad.com/chemical/textile-rice-oil/yarn-count-conversion

Open this case on calc.firecad.com →

Reopens the calculator with the inputs of this report.